MESSMATE





MESSMATE

MESSMATE IS A HIGHLY VERSATILE PRODUCT SUITABLE FOR A VARIETY OF COMMERCIAL AND RESIDENTIAL APPLICATIONS.

Ranging in colour from pale to light brown, this timber offers both character and resilience whilst providing an impressive addition to any project.

Ideal for commercial applications where a light and airy ambience is required.

Messmate is widely used within the residential building industry across various applications including cladding, flooring and bespoke joinery items.

Recognised for its unique grain and rich patina. Messmate adorns many notable projects. With an incredible colour palette and ability to charm any space, Messmate is available to order now.



COMMON NAME

Messmate

LOOK & FEATURES

Medium and even texture with frequent gum veins.

BOTANICAL NAME

Eucalyptus Obliqua

COLOUR

Pale through to light brown.

COMMON USES

A wide range of internal applications including cladding, flooring and bespoke joinery.

PROPERTIES

| DENSITY (KG/M3) | |
|----------------------------|-------------|
| GD | 1080 |
| ADD | 750 |
| HARDNESS KN (JANKA) | |
| Green | 5.3 |
| Dry | 7.1 |
| DURABILITY CLASS | 3 |
| STRENGTH GROUP | S3/SD3 |
| JOINT GROUP | J3/JD3 |
| SHRINKAGE | |
| Radial % (approx.) | > 5.0 |
| Tangential % (approx) | 11.3 |
| STRUCTURAL GRADES | |
| Unseasoned | F11/F14/F17 |
| Seasoned | F22/F27+ |
| TOUGHNESS (NM) | |
| Green | Medium |
| Dry | Medium |
| EARLY FIRE HAZARD INDICES | |
| Ignitability | 13 |
| Spread of Flame | 5 |
| Smoke Development | 3 |
| TERMITE RESISTANT | NR |
| LYCTID SUSCEPTIBLE SAPWOOD | Yes |
| | |

